

LUMAFUSE PETG FILAMENT

RECOMMENDED PRINT SETTINGS



PRINT TEMPERATURE

- The optimal printing range is 240 – 250° C



BED TEMPERATURE

- Up to 85° C



PRINTING SPEED

- Base printing speed of 60 mm/s
- Infill speed of 40 mm/s
- Wall speed of 40 mm/s
- Initial layer speed of 18 mm/s



COOLING

- For stronger parts, turn off the fan. For better feature detail, increase the fan speed, up to 100%.



BED ADHESION

- PETg sticks well to PVA based glue.

If using Ultimaker Cura, enable the LumaFuse PETg material profile available in the Marketplace or manually type in the settings from the information above.

©Lumas Polymers 2025. All Rights Reserved. Confidential and Proprietary. Disclaimer: Due to the large variety of printers and part geometries, the given process parameters are a guideline.

LUMAFUSE PETG FILAMENT

LumaFuse PETg is an easy-processing, standard filament for printing jobs requiring good strength and stiffness along with a good balance of properties in XY and XYZ directions. LumaFuse PETg filament is stronger than PLA. Its toughness and broad operating-temperature range makes it a dependable material for many projects.

APPLICATIONS

- Automotive, aerospace, general manufacturing
- Jigs, fixtures, and tooling
- Housings
- Cosmetics
- Brackets

ADVANTAGES

- Easy printability, very consistent results
- Low shrinkage and warpage
- Post-processing sanding, cutting, or drilling without compromising part
- Good strength and stiffness
- Operating temperature range of -40°C to 80°C
- Excellent chemical resistance

DIAMETERS

- 1.75mm
- 2.85mm



QUESTIONS? VISIT [LUMASPOLYMERS.COM](https://lumaspolymers.com) FOR THE LATEST PRINT PROFILES.